

Product Datasheet: ARC BX1

100% solids, modified epoxy formulation, reinforced with a proprietary blend of ceramic beads and powders for extremely abrasive sliding wear environments. ARC BX1 industrial wear resistant coating is designed to:

- Protect areas exposed to sliding abrasion
- Resurface damaged metal in lieu of more traditional weld overlays
- Replace ceramic tiles and rubber linings which can more easily disbond
- Easily apply by trowel

Application Areas

Packaging and Coverage

Nominal, based on a 6 mm (240 mil) thickness

1.5 liter kit covers 0.25 m² (2.69 ft²)

Note: Components are pre-measured & pre-weighed.

Each kit includes mixing and application instructions

■ 12 kg kit covers 0.82 m² (8.82 ft²)

- Bins and silos
- Apex cones
- Slurry pumps
- Wear plates

plus tools.

Colors: Gray

- Blow lines
- Hydropulpers
- Chutes
- Cyclones

- Pipe elbows
- Exhausters
- Transport screws
- Pneumatic transport lines



Features and Benefits

- Nested, easy to carry package design
 - Easy field or shop use
- High ceramic loading level
 - Extends life of equipment exposed to coarse particle wear
 - Lowers coefficient of thermal expansion
- Chemically resistant polymer matrix
 - Covers a broad range of chemical exposures
- High adhesive strength
 - Resists disbonding
- High build single coat application
 - Allows for vertical build capability to most substrates

3/25

- 100% solids; no VOCs; no free isocyanates
 - Enhances safe use
 - No shrinkage on cure

Technical Data			
Composition Matrix	A modified epoxy resin reacted with an aliphatic curing agent		
Reinforcement	A proprietary blend of ceramic particles selected for resistance to severe sliding wear		
Cured Density		2.3 g/cc	146 lb/ cu.ft.
Pull-Off Adhesion	(ASTM D 4541)	217.2 kg/cm² (21.4 MPa)	3,000 psi
Compressive Strength	(ASTM C 579)	676 kg/cm ²	12,100 psi
Tensile Strength	(ASTM C 307)	280 kg/cm ² (26.9 MPa)	3,600 psi
Flexural Strength	(ASTM C 580)	450 kg/cm² (46 MPa)	7,100 psi
Slurry Abrasion Response (SAR Number)	(ASTM G75)	627	
Impact Resistance (reverse)	(ASTM D 2794)	>10.8 N-m	>160 in-lb.
Shore D Durometer Hardness	(ASTM D 2240)	82	
Vertical Sag Resistance, at 21°C (70°F) and 6 mm (1/4")		No sag	
Maximum Temperature (Dependent on service)	Wet Service Dry Service	95°C 205°C	203°F 400°F
Shelf life (unopened containers)	3 years [stored between 10°C (50°F) and 32°C (90°F) in dry, covered facility]		



A.W. Chesterton Company 860 Salem Street, Groveland, MA 01834 USA Tel +1 978-469-6888 Toll Free 844-469-6888 arcindustrialcoatings.com ARCInfo@Chesterton.com © 2025 AW. Chesterton Company

Registered trademark owned and licensed by A.W. Chesterton Company in USA and other countries, unless otherwise noted.

Technical Data reflect results of laboratory tests and are intended to indicate general characteristics only. Since many actual application circumstances are beyond Chesterton's knowledge and/or control, the product user must determine the suitability of the products it intends to use for its particular purpose and assume all risks and liabilities in connection therewith. CHESTERTON DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form No. 084975 ARC BX1 – English