

Product Datasheet: ARC S4+(E)

100% solids, advanced reinforced thin film coating to protect structures against extreme chemical attack and corrosion. ARC S4+(E) industrial coating is designed to:

- Protect against extreme chemical attack in immersion
- Provide extended wear resistance
- Apply by brush, roller, airless or plural component spraying

Application Areas

- Exhaust gas ductwork Chemical storage tanks
- Heat exchangers
- Fans and housings
- Chimneys & stacks
- Tank linings

Packaging and Coverage

Nominal based on DFT 375 µm (15 mil) Typically applied as 2-Coat System

- 1125 ml cartridge covers 3.00 m² (32.30 ft²)
- 16 liter kit covers 42.70 m² (459.30 ft²)

Note: Components are pre-measured & pre-weighed. Each kit includes mixing and application instructions.

Colors: Gray or red





Features and Benefits

- Multi-functional chemistry
 - Resists concentrated chemicals
- High cross-link density
 - Permeation resistant
 - Improved thermal stability
 - Enhanced mechanical properties
- Spark testable per NACE SP0188
 - Easy post application inspection
 - Facilitates quality assurance
- High adhesive strength
 - No underfilm corrosion
- 100% solids; no VOCs; no free isocyanates
 - Enhances safe use

To all all Date			
Technical Data			
Composition Matrix	A modified epoxy resin reacted with a modified cycloaliphatic amine curing agent		
Reinforcement	Proprietary blend of surface modified mineral reinforcements		
Cured Density		1.3 g/cc	81 lb/ cu.ft.
Flexural Strength	(ASTM D 790)	378 kg/cm ² (37.3 MPa)	5,400 psi
Pull-Off Adhesion	(ASTM D 4541)	337 kg/cm² (33 MPa)	4,800 psi
Tensile Strength	(ASTM D 638)	336 kg/cm² (32.4 MPa)	4,700 psi
Tensile Elongation	(ASTM D 638)	7.9%	
Flexural Modulus	(ASTM D 790)	1.4 x 10 ⁴ kg/cm ² (1412 MPa)	2.0 x 10 ⁵ psi
Shore D Durometer Hardness	(ASTM D 2240)	82	
Vertical Sag Resistance, at 21°C (70°F) and 250 μm (10 mil)		No sag	
Maximum Temperature (Dependent on service)	Wet Service Dry Service	50°C 110°C	117°F 220°F
Shelf life (unopened containers)	3 years [stored between 10°C (50°F) and 32°C (90°F) in dry, covered facility]		



02/2025

^{© 2025} A.W. Chesterton Company

[®] Reaistered trademark owned and licensed by A.W. Chesterton Company in USA and other countries, unless otherwise noted.